

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Terra Mater Hardwood Floors
23-27 Rodeo Drive
Dandenong VIC 3175

Test Number : 17-005707
Issue Date : 18/10/2017
Print Date : 24/10/2017

Sample Description Vinyl plank flooring

**AS 2834-1995
Appendix D**

Surface Resistance of Flooring Systems Computer Accommodation - Guidelines for the Control of Static Electricity

Temperature 18
Relative Humidity 40

Specimen	Length
1	5 Gigaohms
2	5 Gigaohms
3	4 Gigaohms
4	5 Gigaohms
5	6 Gigaohms
6	4 Gigaohms
7	5 Gigaohms
8	4 Gigaohms
Mean	5 Gigaohms

Samples were conditioned for a minimum of 48 hours prior to measurement at $20\pm 2^{\circ}\text{C}$ and $40\pm 3\%$ relative humidity.

No width measurement due to size of specimen.

108721

23054

Page 1 of 2

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Terra Mater Hardwood Floors
23-27 Rodeo Drive
Dandenong VIC 3175

Test Number : 17-005707
Issue Date : 18/10/2017
Print Date : 24/10/2017

AS 2834-1995
Appendix D

Bulk Resistance of Flooring Systems Computer Accommodation - Guidelines for the Control of Static Electricity

Temperature	20 °C
Relative Humidity	40 %
Specimen	
1	4 Gigaohms
2	7 Gigaohms
3	7 Gigaohms
4	5 Gigaohms
5	4 Gigaohms
6	4 Gigaohms
7	5 Gigaohms
8	4 Gigaohms
Mean	5 Gigaohms

Samples were conditioned for a minimum of 48 hours prior to measurement at 20±2°C and 40±3% relative humidity.

108721

23054

Page 2 of 2

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR